

(A1) an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of an olefin-unsaturated carboxylic acid random copolymer and an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, and

(A2) a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of a metal ion-neutralized olefin-unsaturated carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

517  
C17  
(B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

B'  
(C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.

13. A solid golf ball comprising a solid core of at least one layer and a cover of at least one layer enclosing the solid core, wherein at least one layer of the solid core or the cover is made of a golf ball material comprising a heated mixture having a melt index of at least 1.0 dg/min which is composed of:

(A) 100 parts by weight of a base resin comprising one or a mixture of

(A1) an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of an olefin-unsaturated carboxylic acid random copolymer and an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, and

(A2) a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of a metal ion-neutralized olefin-unsaturated

carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

(B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

(C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.

B<sup>1</sup>  
14. The solid golf ball of claim 13 comprising a one-layer cover enclosing the solid core, wherein the cover is made of the golf ball material.

15. The solid golf ball of claim 13 comprising a cover of at least two layers enclosing the solid core, wherein at least one inner cover layer other than the outermost cover layer is made of the golf ball material.

16. A thread-wound golf ball comprising:  
a thread-wound core composed of a solid center of at least one layer or a liquid center made of a liquid-filled center envelope, about which solid or liquid center has been wound a rubber thread, and

SUB  
C7  
a cover of at least one layer which encloses the thread-wound core;  
wherein the solid center or at least one layer of the cover is made of a golf ball material comprising a heated mixture having a melt index of at least 1.0 dg/min which is composed of:

(A) 100 parts by weight of a base resin comprising one or a mixture of

(A1) an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of an olefin-unsaturated carboxylic acid random copolymer and an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, and

(A2) a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of a metal ion-neutralized olefin-unsaturated carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

B<sup>1</sup> (B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

(C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.

17. The thread-wound golf ball of claim 16, wherein the thread-wound core is enclosed within a one-layer cover made of the golf ball material.

18. The thread-wound golf ball of claim 16, wherein the thread-wound core is enclosed within a cover having at least two layers, of which at least one inner layer other than the outermost layer is made of the golf ball material.